

	TYPICAL DATA SHEET*		ISSUE DATE	Feb-17
	GRADE		WWW.TPCO.IR	
	LL0220KJ		IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

LL0220KJ is linear low density polyethylene copolymer containing butene-1(C4) as comonomer.It is suitable for blending with conventional LDPE for blown film applications.

Film made from pure LL0220KJ has the following advantages over LDPE:

good balance of mechanical properties,good optical properties,easy opening properties in 2 layer film.This grade has food contact approval

Applications:

light and medium duty films with good optical properties.

PROPERTY	UNIT	TEST METHOD	TYPICAL VALUE
MELT FLOW INDEX(190°C 2.16KG)	g/10min	ASTM D-1238	2.4
DENSITY	gr/cm3	ASTM D-1505	0.921
VICAT SOFTENING POINT	°C	ASTM D-1525	100

FILM**

DART DROP IMPACT	METHOD A	GR	ASTM D-1709	90
TENSILE STRESS AT YEILD	MD/TD	MPA	ASTM D-882	10/11
TENSILE STRESS AT BREAK	MD/TD	MPA	ASTM D-882	30/25
ELONGATION AT BREAK	MD/TD	%	ASTM D-882	1000/1100
WHITENESS INDEX	-	%	ASTM E-313	50
GLOSS(45°)	-	%°	ASTM D-2457	30

*All above mentioned data are typical values and not to be construed as real specifications.Users should confirm results by their own tests.For more information about guaranteed items, please refer to S.S.S.(Standard Sales Specifications)

**38µm blown film with blow up ratio 2:1,225°C melt temperature , MD: Machine Direction,TD:Transverse Direction

Grade Suffix(Additives Indication):

KJ:GENERAL ANTIOXIDANT WITH SLIP AGENT/ANTIBLOCKING AGENTS