



# RANPELEN J-550S

### PP RANDOM COPOLYMER

### **General Information**

### Description

J-550S is a nucleated random copolymer for injection molding applications. This grade is designed to be processed in conventional injection molding equipment and offers high transparency, good stiffness/impact strength balance, high gloss, high hinge property and low smell. J-550S is a 'Phthalate-Free' product.

# Applications

- Cosmetics container & cap, Food container, Transparency case, Stationery
- Water purifier parts

	Physical Properties <sup>1</sup>					
Physical	Test Method		Nominal Values			
Melt Flow Index	ASTM D1238	12	g/10min			
Density	ASTM D792	0.9	g/cm <sup>3</sup>			
Mechanical						
Tensile Stress (Yield)	ASTM D638	330	kgf/cm <sup>2</sup>	32	MPa	
Tensile Strain (Break)	ASTM D638	>100	%	>100	%	
Flexural Modulus	ASTM D790	13,000	kgf/cm <sup>2</sup>	1,270	MPa	
Rockwell Hardness	ASTM D785	95	R			
Impact						
Notched Izod Impact Strength (23℃)	ASTM D256	5.5	kgf·cm/cm	54	J/m	
Notched Izod Impact Strength (-10℃)	ASTM D256	3.0	kgf·cm/cm	29	J/m	
Thermal						
Heat Deflection Temperature (4.6kgf/cm²)	ASTM D648	95	°C			
Additional Properties						
Haze	ASTM D1003	25	%			
NOTE ISO 9001, 14001, /TS 1						

<sup>&</sup>lt;sup>1</sup> Physical Properties : these are not to be construed as specifications

www.lottechem.com





# RANPELEN J-550S

# PP RANDOM COPOLYMER

### **General Information**

### Description

J-550S is a nucleated random copolymer for injection molding applications. This grade is designed to be processed in conventional injection molding equipment and offers high transparency, good stiffness/impact strength balance, high gloss, high hinge property and low smell. J-550S is a 'Phthalate-Free' product.

# Applications

- Cosmetics container & cap, Food container, Transparency case, Stationery
- Water purifier parts

Physical Properties <sup>1</sup>					
Test Method		Nominal Values			
ISO 1133	12	g/10min			
ISO 1183	0.9	g/cm <sup>3</sup>			
ISO 527-1	300	kgf/cm <sup>2</sup>	29	MPa	
ISO 527-1	>100	%	>100	%	
ISO 178	10,500	kgf/cm <sup>2</sup>	1,030	MPa	
ISO 180	5.0	kgf·cm/cm	49	J/m	
ISO 180	2.5	kgf·cm/cm	24	J/m	
ISO 75-1	85	°C			
	25	%			
NOTE			ISO 9001, 1400	1, /TS 169 <u>49</u>	
	Test Method ISO 1133 ISO 1183 ISO 527-1 ISO 527-1 ISO 178 ISO 180 ISO 180	Test Method  ISO 1133 12  ISO 1183 0.9  ISO 527-1 300  ISO 527-1 >100  ISO 178 10,500  ISO 180 5.0  ISO 180 2.5	Test Method         Nominal V           ISO 1133         12 g/10min           ISO 1183         0.9 g/cm³           ISO 527-1         300 kgf/cm²           ISO 527-1         >100 %           ISO 178         10,500 kgf/cm²           ISO 180         5.0 kgf·cm/cm           ISO 180         2.5 kgf·cm/cm           ISO 75-1         85 ℃	Test Method       Nominal Values         ISO 1133       12       g/10min         ISO 1183       0.9       g/cm³         ISO 527-1       300       kgf/cm²       29         ISO 527-1       >100       %       >100         ISO 178       10,500       kgf/cm²       1,030         ISO 180       5.0       kgf·cm/cm       49         ISO 180       2.5       kgf·cm/cm       24         ISO 75-1       85       ℃	

www.lottechem.com

<sup>1</sup> Physical Properties : these are not to be construed as specifications