

LG411

Styrene-Butadiene-Styrene

Description

Radial structure, Non-Oil Extended Grade
Thermoplastic Elastomer

Application

Asphalt Modifier, Plastic Modifier,
Compounding, Adhesives etc

Physical properties	Unit	Specification	Test method
Density	g/cm ³	0.94	ISO 2781
Volatile material	wt%	Max. 0.5	ASTM D1416
Styrene content	%	31	LSYQS1D011 ³⁾
Mechanical Properties			
Melt index ¹⁾	g/10min	< 1	ASTM D1238
Hardness	Shore A	84	ASTM D2240
T.S.V. ²⁾	cst	28.4	ASTM D445
Other			
Appearance	-	Pellet	-
Structure	-	Radial	-

1) Melt Index: 200°C, 5kg

2) T.S.V.: Toluene Solution Viscosity 5%

3) LG Chem Test Method

- For more information. Please kindly keep in touch with us.
- Address. LG twin towers 20, Yoido-dong, seoul, 150-606, korea.
- Tel) 82-2-3773-3615, Fax) 82-2-3773-7660